

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE 1 Jan 98	3. REPORT TYPE AND DATES COVERED Final Report 1/6/89-9/30/97		
4. TITLE AND SUBTITLE Development of Elastomeric Polypeptide Biomaterials		5. FUNDING NUMBERS N00014-89-J-1970		
6. AUTHOR(S) Dr. Dan W. Urry				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Laboratory of Molecular Biophysics University of Alabama at Birmingham PO Box 300 University Station Birmingham, AL 35294-0019		8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 800 N. Quincy St. Arlington, VA 22217-5000		10. SPONSORING / MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Distribution Unlimited		12b. DISTRIBUTION CODE		
<p>13. ABSTRACT (Maximum 200 words) Using a diverse set of experimental observations on a family of elastomeric protein-based polymers, five axioms have been developed which govern protein function and engineering by means of hydrophobic folding and assembly. Furthermore, the underlying physical process has also been experimentally demonstrated to be competition for hydration between hydrophobic and polar moieties. These developments represent the nuts and bolts of amphiphilic polymer structure formation, function and engineering by means of hydrophobic folding and assembly.</p> <p>Basically, amphiphilic polymers, including proteins and protein-based polymers, exhibit hydrophobic folding and assembly (phase) transitions with the onset occurring as the temperature is raised above a value designated as T_t. The value of T_t is determined by the amount of hydrophobic hydration, the more hydrophobic hydration the lower the value of T_t and the less hydrophobic hydration the higher the value of T_t.</p> <p>This mechanism of apolar-polar repulsive free energy of hydration, which controls hydrophobic folding and assembly, can be argued to be a more efficient mechanism for free energy transduction than the more commonly considered charge-charge interaction mechanism. Therefore, the axioms and the underlying physical process represent fundamental developments in the capacity to design amphiphilic polymers for diverse functions, generally categorizable as free energy transduction.</p>				
14. SUBJECT TERMS protein-based polymers, free energy transduction, inverse temperature transitions, hydrophobic folding and assembly, apolar-polar repulsive free energy of hydration			15. NUMBER OF PAGES	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

FINAL REPORT

Grant #: N00014-89-J-1970

R&T Code: 3412-016

PRINCIPAL INVESTIGATOR: Dr. Dan W. Urry

INSTITUTION: The University of Alabama at Birmingham

GRANT TITLE: Development of Elastomeric Polypeptide Biomaterials

AWARD PERIOD: 1 June 1989 - 30 September 1997 (8 and 1/3 years)

OBJECTIVE: To design elastomeric polypeptide biomaterials in order to achieve diverse forms of free energy transduction by these water-miscible hydrophobic folding and assembling macromolecules, thereby to elucidate the underlying mechanisms and principles, and therefrom to make possible new materials and applications.

APPROACH: To design protein-based polymers capable of energy conversions involving mechanical, pressure, thermal, chemical, electrical, and electromagnetic energies, due to their capacity to exhibit inverse temperature transitions of hydrophobic folding and assembly as the temperature is raised over a characteristic temperature interval, the onset of which is designated as T_t .

The protein-based polymers are prepared by means of recombinant DNA technology. The products are purified utilizing the inverse temperature transitional properties of the polymers and verified by the standard physical and chemical means and by biological testing.

The primary purpose of the designed and prepared protein-based polymers was to demonstrate, ultimately, all fifteen pair-wise free energy transductions involving the above six energies. Polymers also can be prepared to demonstrate a very important sixteenth, chemo-chemical, transduction.

MAJOR ACCOMPLISHMENTS: (8 and 1/3 years)

General Perspective: The hydrophobic effect, or hydrophobic folding, has long been appreciated as relevant to protein structure and function. Until this work, there has not been a systematic development of what controls hydrophobic folding nor has there been a reasonable assessment of just how important hydrophobic folding is in protein structure and function. An elastomeric model protein system was used where the many factors controlling hydrophobic folding could be isolated, demonstrated and evaluated and where those factors could be used in de novo designs to achieve function.

It has also long been appreciated that raising the temperature to arrive at a functional protein structure is indicative of hydrophobic folding, as occurs on raising the temperature of a cold denatured protein. Using the special family of elastomeric model proteins that exhibit a phase transition of hydrophobic folding and assembly, we have carefully assessed the hydrophobic folding and assembly process in terms of the temperature for the onset of folding, T_t . The result has been the experimental development of a set of five axioms for protein function and engineering.

Remarkably, using specific designs of our model protein system, virtually every pair-wise energy conversion of metabolism can be demonstrated. This is achieved by means of controlling the temperature of the hydrophobic folding and assembly transition. It involves interconversion of the free energies, the intensive variables of which are - mechanical force, pressure, temperature, chemical potential, electrical potential and electromagnetic radiation. More explicit demonstrations utilize designed model proteins and corresponding energy inputs of heat, chemical energy, pressure, electrochemical energy, and light to drive contraction in visual demonstration of the mechanical energy output of lifting a weight. This is documented in part by a video of designed elastomeric model proteins "pumping iron."

Having demonstrated the phenomenology of changing protein structure and attaining function by means of controlling hydrophobic folding and assembly, it became possible to determine the underlying physical process. It is one of competition for hydration between apolar

(hydrophobic) and polar (e.g., charged) groups constrained to coexist along a protein chain sequence, rather than being free to separate as oil from vinegar. The technical details are developed below.

Stepwise Experimental Development of the Phenomenology:

The initial experimental observation was that T_t decreases for more hydrophobic residues and increases for more polar residues. This is the basis for a T_t -based hydrophobicity scale. This is **Axiom 1**. By independent measurement, using microwave dielectric relaxation, the value of T_t is found to be a measure of the amount of hydrophobic hydration. Since hydrophobic association can be observed as a phase transition, $T_t \approx \Delta H_t / \Delta S_t$. The ratio for hydrophobic hydration has been experimentally observed to be smaller (corresponding to a lower value of T_t) for more hydrophobic hydration and larger (corresponding to a higher value of T_t) for less hydrophobic hydration.

Raising the temperature from below to above T_t drives hydrophobic folding and assembly. When the model elastic proteins are cross-linked into an elastomeric band and the temperature is raised from below to above T_t , the band contracts and lifts a weight. This somewhat obvious demonstration of thermo-mechanical transduction represents **Axiom 2**.

Controlling the value of T_t controls the hydrophobically folded and assembled state of the protein. Essentially every variable (energy input) imposed upon an aqueous system containing an appropriately designed model protein changes the value of T_t . Lowering the temperature from above to below an operating temperature drives hydrophobic folding and assembly at constant temperature, and can be used to do mechanical work of lifting a weight when the polymer is cross-linked as an elastic matrix. This is **Axiom 3**. A video has been prepared showing different energy inputs, that lower T_t from above to below an operating temperature, to drive contraction and to perform the mechanical work of lifting a weight.

Any two different energy inputs, which with the properly designed elastic model protein can individually drive hydrophobic folding and assembly by lowering T_t , can be converted one into the other by being part of the same hydrophobic folding domain. This is **Axiom 4**. An example is the conversion of the electrical energy of the reduction of a redox couple into the chemical energy of picking up a proton due to the shift in pKa of the chemical couple caused by formation of the more hydrophobic reduced state. This is an example of electro-chemical transduction as occurs in the development of a proton gradient during electron transport in the inner mitochondrial membrane.

Axiom 5 is the experimental demonstration that energy conversion by this mechanism is more efficient for more hydrophobic domains, hence one of the advantages of oxidative phosphorylation occurring within a lipid bilayer membrane. An experimental basis for this statement resides in the observation of supra-linear hydrophobic-induced pKa shifts discussed below.

Stepwise Experimental Development of the Physical Basis:

Implication of Dependence of T_t on Hydrophobicity and Charge: On the one hand, adding a CH_2 moiety to a repeating peptide whether a repeating pentapeptide, e.g., $(\text{GVGVP})_n$ going to $(\text{GVGIP})_n$ or a repeating tetrapeptide, e.g., $(\text{GGVP})_n$ going to $(\text{GGIP})_n$, lowers the value of T_t . On the other hand, removing two CH_2 moieties, as in going from $(\text{GGVP})_n$ to $(\text{GGAP})_n$ or in going from $(\text{GVGVP})_n$ going to $(\text{GAGVP})_n$, increases the value of T_t . It is straightforward to deduce that the larger aliphatic moieties would have more water of hydrophobic hydration and that the smaller aliphatic moiety would have less hydrophobic hydration. Furthermore, the formation of a few carboxylates per 100 residues of poly[0.8(GVGVP),0.2(GEGVP)] dramatically increases the value of T_t . One proposes from this initial finding that lower values of T_t indicate greater hydrophobicity with more hydrophobic hydration and higher values of T_t indicate lesser hydrophobicity with less hydrophobic hydration and that the formation of anionic carboxylates destroys hydrophobic hydration. This putative relationship is established below by a series of experimental results.

Differential Scanning Calorimetry (DSC): Effect of charge on the heat of the hydrophobic folding and assembly transition: Since the work of Frank and Evans in 1945, one appreciates that dissolution of a hydrophobic group in water is an exothermic reaction and that solubility is limited due to the formation of low entropy, water structure surrounding the hydrophobic group. Accordingly, ΔH is negative and ΔS is positive, resulting in a small value of the Gibbs free energy, $\Delta G = \Delta H - T\Delta S$. To the extent that hydrophobic folding in a model protein can be represented as a reversal of hydrophobic dissolution, the endothermic heat required to drive hydrophobic folding represents the heat required to destructure hydrophobic hydration. Using poly[0.8(GVGVP),0.2(GEGVP)], the heat of the endothermic transition of hydrophobic folding and assembly decreases to one-fourth as two carboxylates form per 100 residues. The smaller ΔH suggests less hydrophobic hydration and hydration of the carboxylate anion occurs at the expense of hydrophobic hydration. This is consistent with a mechanism of competition for hydration between hydrophobic and charged moieties constrained to coexist along a polymer chain.

Stretch-induced pKa shifts: The first compelling insight, that a mechanism other than electrostatic charge-charge repulsion was operative for mechano-chemical transduction exhibited by these elastic protein-based polymers, came on determining the glutamic acid pKa resulting from stretching a hydrophobically folded elastic band of γ -irradiation cross-linked poly[0.8(GVGVP),0.2(GEGVP)]. Stretching increased the pKa of the Glu residue carboxyl from about 4 to above 9 and resulted in a supra-linear increase in pKa with increase in mechanical force. In terms of change in chemical potential, $\Delta\mu$, and change in applied force, Δf , the experimentally determined $\partial\mu/\partial f < 0$, whereas for charge-charge repulsion the sign is reversed, $\partial\mu/\partial f > 0$. This means that in spite of an increase in water in the elastic model protein band on stretching, the carboxylate increases in free energy, i.e., becomes energetically less favored. It is clear that the dominant change in hydration on stretching a hydrophobically folded elastic band would be the formation of water of hydrophobic hydration. The conclusion becomes that hydrophobic hydration is unsuited for carboxylate hydration and that in order to achieve its own hydration the carboxylate must pay for the energy required to destructure hydrophobic hydration. If this is correct, then step-wise increasing hydrophobicity of an elastic model protein should systematically increase carboxyl pKa.

Hydrophobic-induced pKa shifts: Systematically replacing an ionizable residue in poly[f_v (GVGIP), f_x (GXGIP)] where $f_v + f_x = 1$ and X is either Glu (E), Asp (D) or Lys (K) by a hydrophobic Val residue causes the carboxyl pKa values to remarkably increase as f_E and f_D approach zero and the amino pKa values of Lys to decrease as f_K approaches zero. Furthermore, in the family of model proteins, (GVGVP GVG β P GXG β P GVGVP GVG β P G β G β P) $_n$, where X may be either E or D and where β may be either V or F (Phe) and where the number of Phe residues are 0, 2, 3, 4, or 5, a supra linear increase in pKa occurs as F goes from 0 to 5. Indeed, two different types of model protein systems involving three different functional groups demonstrated supra-linear increases in pKa shifts as hydrophobicity is stepwise increased. Hydrophobic-induced pKa shifts are more effective than electrostatic-induced pKa shifts when utilized in performance of chemo-mechanical transduction. *More hydrophobic hydration present in an unfolded polymer causes greater pKa shifts to be exhibited by the ionizable functions of the polymer!*

Proposal of an apolar-polar repulsive free energy of hydration, ΔG_{ap} : Progressive increases in hydrophobicity progressively raise the free energy of charged side chains as reflected in the above noted progressive increases in pKa shifts. As long as T_t is above 0C, the pKa shifts are seen without any change in state. Hydrophobic-induced pKa shifts can be observed while the model protein remains in the fully hydrated unfolded and unassembled state. Thus, the pKa shift can not be ascribed to the change in dielectric constant on going from solution into a folded state. This means that, when a charged species is

tethered to a hydrophobic species, the two species will be positioned in order to achieve the most hydration unaltered by the other species. In order that each species will have the maximal hydration, the lowest free energy at values below T_c for the model protein, they will occupy the most distant positions allowed by their tether. In other words, there exists an apolar polar repulsive free energy of hydration.

One measure of this apolar polar repulsive free energy is the magnitude of the pKa shifts. Since the chemical potential, μ , is given by $\mu = RT \ln a$ where a is the activity, and since at normal values of pH, $a = [H^+]$, $\mu = 2.3RT \log [H^+] = -2.3 RT \text{ pH}$. The change in chemical potential, $\Delta\mu$, resulting from a shift in pKa, becomes $\Delta\mu = -2.3RT \Delta pK_a$. As chemical potential is Gibbs free energy per mole, $\Delta G/\Delta n$, the increase in free energy due to the apolar-polar repulsive free energy of hydration, ΔG_{ap} , is $2.3RT \Delta pK_a$. Since hydrophobic-induced pKa shifts as large as 6 pH units have been observed in designed model proteins, a repulsive free energy of greater than 8 kcal/mole has been experimentally observed. This is the magnitude of free energy change whereby much of protein function occurs.

Direct observation of the water of hydrophobic hydration: Using microwave dielectric relaxation to examine the behavior of water in model proteins capable of hydrophobic folding and assembly transitions, a relaxation due to water is observed near 5 GHz, some 10 GHz below that of bulk water. This 5 GHz water results from interacting with the model protein; it increases on making the model protein more hydrophobic, and it disappears as the model protein hydrophobically folds and assembles. Therefore, it is water of hydrophobic hydration!

The key question now becomes, what happens to this hydrophobic hydration on ionization of carboxylates within the model protein. The answer, two-thirds of the water disappears as less than two carboxylates form per 100 residues of model protein. This confirms interpretation of the above-described DSC results where three-fourths of the heat of the endothermic hydrophobic folding and assembly transition disappeared on formation of less than two carboxylates per 100 residues. Thus, the microwave dielectric relaxation data constitute direct observation of the competition for hydration between apolar and polar moieties!

CONCLUSIONS: By means of this support we have: 1) experimentally developed five axioms for protein function and engineering by means of hydrophobic folding and assembly transitions, 2) demonstrated the physical basis underlying the "hydrophobic effect" to be an apolar-polar repulsive free energy of hydration, which can be estimated in specific cases by means of hydrophobic-induced pKa shifts, 3) a priori designed model proteins capable of performing diverse energy conversions (free energy transductions) of biology, 4) provided data, which argues that protein function by controlling hydrophobic folding and assembly represents a far more efficient process than the commonly considered charge-charge interaction mechanism, 5) noted parallel phenomena with a number of biological systems, implying relevance to protein function in biology, and 6) used the above knowledge to develop medical and non-medical applications with feasibility demonstrated for both areas and with some 30 US patents issued and/or filed.

SIGNIFICANCE: The five axioms for protein function and engineering and the underlying physical process of competition for hydration between hydrophobic and polar moieties represent the nuts and bolts of protein function by means of hydrophobic folding and assembly. A systematic and comprehensive understanding of the role of hydrophobic folding and assembly in protein structure and function has been developed. Controlling hydrophobic folding and assembly can be argued to be a more efficient mechanism for free energy transduction than charge-charge interaction. The axioms for hydrophobic folding and assembly in protein function and the underlying physical process represent fundamental developments in understanding protein function and engineering.

AD NUMBER	DATE	DTIC ACCESSION NOTICE
1. REPORT IDENTIFYING INFORMATION		REQUESTER: 1. Put your mailing address on reverse of form. 2. Complete items 1 and 2 3. Attach form to reports mailed to DTIC. 4. Use unclassified information only 5. Do not order document for 6 to 8 weeks
A. ORIGINATING AGENCY Office of Naval Research		
B. REPORT TITLE AND/OR NUMBER Development of Elastomeric Polypeptide Biomaterials		
C. MONITOR REPORT NUMBER		
D. PREPARED UNDER CONTRACT NUMBER N00014-89-J-1970		
2. DISTRIBUTION STATEMENT Unlimited		DTIC: 1. Assign AD Number 2. Return to requester

DTIC Form 50
JUL 96

PREVIOUS EDITIONS ARE OBSOLETE

Dr. Dan W. Urry
Laboratory of Molecular Biophysics
PO Box 300 University Station
Birmingham, Alabama 35294-0019

PATENT INFORMATION:

*f. Patents Issued and Pending since January 1995 (time of last competitive renewal)

D. W. Urry Polymers Responsive to Electrical Energy	European Application PCT/US96/09776 U. S. Application CIP (to #19-A)	0830509 Pending	Issued 3/25/98 Filed 06/07/96 Filed 06/07/95
D. W. Urry, David A. Tirrell, and Catherine Jean Heimbach Photoresponsive Polymers	U.S. Application CIP Serial 08/481,179 (Serial 08/482,179 filed 06/07/95, abandoned 04/06/98 in favor of 09/032/373)	Pending	Filed 06/07/95
D. W. Urry, David A. Tirrell, and Catherine Jean Heimbach Photoresponsive Polymers	U.S. Application CIP Serial 08/485,426	Pending	Filed 06/07/95
D. W. Urry, et. al. Elastomeric Polytetrapeptide Matrices Suitable for Preventing Adhesion of Biologic Materials	U.S. Application CIP Serial 08/485,495	5519004	Issued 05/21/96 Filed 06/07/95
D. W. Urry U. S. Application A Simple Method for the Purification of a Bioelastic Polymer	U.S. Application Serial 08/543,020 (Serial 08/423,516 filed 4/14/95, abandoned 6/14/96 in favor of 08/543,020) International Application PCT/US96/05186 (originally filed 04/15/96 as WO, abandoned) Elected Japan & filed JP application 8-531261	5954387	Issued 12/29/98 Filed 10/13/95 Filed 04/14/97
D. W. Urry, et. al. Elastomeric Polypeptide Matrices for Preventing Adhesion of Biologic Materials	U.S. Application Serial 08/246,874	5,527,610	Issued 06/18/96 Filed 05/20/94
D.W. Urry Superabsorbent Materials	Japanese Application 1-5050221 U.S. Application CIP Serial 08.384,566	2115962 5520672	Issued 12/06/96 Filed 05/20/95 Issued 05/28/96 Filed 02/06/95
D.W. Urry, et. Al Photoresponsive Polymers	U.S. Application Serial 08/187,441	Pending	Filed 01/24/94
D.W. Urry Bioelastomeric Drug Delivery System	U. S. Application Serial #08/316,802 European Application 91302648.0	Pending EP 0449592	Filed 10/03/94 Issued 11/30/94 Filed 10/03/94
	Japanese Application	1994740	Issued 11/22/95

	3-63253/87		Filed 10/03/94
D.W. Urry	U.S. Application	5393602	Issued 02/28/95
Superabsorbent Materials	Serial 07/688,185		Filed 04/19/91
	European Application	Pending	Filed 03/10/93
	92.917457.1		
	Japanese Application	Pending	Filed 03/10/92
	4-510189		
D.W. Urry	U.S. Application	4,898,926	Issued 02/06/90
Bioelastomer Containing Tetra/	PCT/US 88/10949		Filed 06/15/87
Pentapeptide Units	Japanese Application	Pending	Filed 12/15/89
	63-50213		
D. W. Urry and K.U.M. Prasad	Japanese Application	2085090	Issued 08/23/96
Segmented Polypeptide Bioelastomers	503100/87		Filed 04/17/87
to Modulate Elastic Modulus	U.S. Application	4870055	Issued 09/26/89
			Filed 04/08/88
	(originally filed 4/17/86)		
	European Application	EP 0302892	Issued 07/13/94
	87.903490.8		Filed 4/08/88

PUBLICATIONS:

1. Dan W. Urry, Asima Pattanaik, Jie Xu, T. Cooper Woods, David T. McPherson and Timothy M. Parker, "Elastic Protein-based Polymers in Soft Tissue Augmentation and Generation," *J. Biomater. Sci. Polymer Edn*, 9, 1015-1048 (1998).
2. Dan W. Urry, "Five Axioms for the Functional Design of Peptide-Based Polymers as Molecular Machines and Materials: Principle for Macromolecular Assemblies," *Biopolymers (Peptide Science)*, 47, 167-178 (1998).
3. Chi-Hao Luan and Dan W. Urry, "Elastic, Plastic, and Hydrogel-forming Protein-based Polymers," invited article for the *Polymer Data Handbook*, (Oxford University Press, New York) (ed. J. E. Mark), 1999, pp. 78-89.
4. Dan W. Urry, ShaoQuing Peng, Chi-Hao Luan, Chi-Xiang, Luan, Asima Pattanaik, Jie Xu, David T. McPherson, "Hydrophobic Hydration in Protein Models for Muscle Contraction: Calcium Ion, Thermal, Stretch and pH Activation," *Scanning Microscopy International*, 1999. (In press)
5. Dan W. Urry, "Five Axioms for Protein Engineering: Keys for Understanding Protein Structure/Function?," American Peptide Symposium, 1997, in press.
6. Dan W. Urry, "Physical Chemistry of Biological Free Energy Transduction as Demonstrated by Elastic Protein-based Polymers," invited FEATURE ARTICLE, *J. Phys. Chem.B*, 101, 11007-11028, 1997.
7. Dan W. Urry, "Engineering Protein-based Machines to Emulate Key Steps of Metabolism (Biological Energy Conversion)" *Biotechnology and Bioengineering*, 58, 175-190, 1998.
8. Dan W. Urry and Asima Pattanaik, "Elastic Protein-based Materials in Tissue Reconstruction," *Annals NY Acad Sci.*, 831, 32-46, 1997.
9. Dan W. Urry, "On the Molecular Structure, Function and Pathology Of Elastin: The Gotte Stepping Stone," In: *The Structure, Function and Pathology of Elastic Tissue*, Tip. Mario Armento & Co. Publisher, via Vaccaro, 48, Potenza, Italy, 11-22, 1997.
10. X. Zhang, D. W. Urry, and H. Daniell, "Expression of an Environmentally Friendly Synthetic Protein-based Polymer Gene in Transgenic Tobacco Plants," *Plant Cell Reports* 16:174-179, 1996.
11. Dan W. Urry, ShaoQing Peng, Jie Xu, and David T. McPherson, "Characterization of Waters of Hydrophobic Hydration by Microwave Dielectric Relaxation," *JACS* 119, 1161-1162, 1997.
12. Dan W. Urry, "Engineers of Creation," *Chemistry in Britain*, 39-42, 1996.
13. Dan W. Urry, Larry C. Hayes, and Shao Qing Peng, "Designing for Advanced Materials by the DT_t-Mechanism," *SPIE-The International Society for Optical Engineering Smart Structures and Materials 1996 - Smart Materials Technologies and Biomimetics*, San Diego, CA, 2716, 343-346, 1996.
14. Dan W. Urry, Asima Pattanaik, Mary Ann Accavitti, Chi-Xiang Luan, David T. McPherson, Jie Xu, D. Channe Gowda, Timothy M. Parker, Cynthia M. Harris, and Naijie Jing, "Transductional Elastic and Plastic Protein-based Polymers as Potential Medical Devices," in

Handbook of Biodegradable Polymers, ed. by Domb, Kost, and Wiseman, Harwood Academic Publishers, Chur, Switzerland, pp. 367-386, 1997.

15. X. Zhang, C. Guda, R. Datta, R. Dute, D. W. Urry, and H. Daniell, "Nuclear Expression of an Environmentally Friendly Synthetic Protein-based Polymer Gene in Tobacco Cells," *Biotech Letters* 17(12), 1279-1284, 1995.
16. David T. McPherson, Jie Xu, and Dan W. Urry, "Product Purification by Reversible Phase Transition Following *E. coli* Expression of Genes Encoding up to 251 Repeats of the Elastomeric Pentapeptide GVGVP," *Protein Expression and Purification* 7, 51-57, 1996.
17. Dan W. Urry and Chi-Hao Luan, "Proteins: Structure, Folding and Function," In Bioelectrochemistry: Principles and Practice (Giorgio Lenaz, Vol. Ed.), Birkhäuser Verlag AG, Basel, Switzerland, pp. 105-182, 1995.
18. Dan W. Urry and ShaoQing Peng, "Non-linear Mechanical Force-induced pKa Shifts: Implications for Efficiency of Conversion to Chemical Energy," *J. Am. Chem. Soc.*, 8478-8479, 1995.
19. Dan W. Urry, Larry C. Hayes, D. Channe Gowda, ShaoQing Peng and Naijie Jing, "Electro-chemical Transduction in Elastic Protein-based Polymers," *Biochem. Biophys. Res. Commun.*, 210, 1031-1039, 1995.
20. D. Channe Gowda, Chi-Hao Luan, Raymond L. Furner, ShaoQing Peng, Naijie Jing, Cynthia M. Harris, Timothy M. Parker, Dan W. Urry, "Synthesis and Characterization of Human Elastin W₄ Sequence," *Int. J. Pept. Protein Res.*, 46, 453-463, 1995.
21. Dan W. Urry, D. Channe Gowda, ShaoQing Peng and Timothy M. Parker, "Non-linear Hydrophobic-induced pKa Shifts: Implications for Efficiency of Conversion to Chemical Energy," *Chem. Phys. Letters*, 239, 67-74, 1995.
22. Naijie Jing and Dan W. Urry, "Ion Pair Binding of Ca⁺⁺ and Cl⁻ Ions in Micellar-packaged Gramicidin A," *Biochem. Biophys. Acta*, 1238, 12-21, 1995.
23. Naijie Jing, Kari U. Prasad, and Dan W. Urry, "The Determination of Binding Constants of Micellar-packaged Gramicidin A by ¹³C and ²³Na NMR," *Biochem. Biophys. Acta*, 1238, 1-11, 1995.
24. D. W. Urry, Cynthia M. Harris, Chi Xiang Luan, Chi-Hao Luan, D. Channe Gowda, Timothy M. Parker, ShaoQing Peng, and Jie Xu, Chapter entitled "Transductional Protein-based Polymers as New Controlled Release Vehicles," Part VI: New Biomaterials for Drug Delivery, in Controlled Drug Delivery: The Next Generation, (Kinam Park, ed.) Am. Chem. Soc. Professional Reference Book, pp. 405-437, 1997.
25. C. Guda, X. Zhang, D. T. McPherson, J. Xu, J. H. Cherry, D. W. Urry, and H. Daniell, "Hyper Expression of an Environmentally Friendly Synthetic Polymer Gene," *Biotechnology Letters* 17, 745-750, 1995.
26. D. W. Urry, C.-H. Luan, C. M. Harris, T. Parker, "Protein-based Materials with a Profound Range of Properties and Applications : The Elastin DT_t Hydrophobic Paradigm," In Proteins and Modified Proteins as Polymeric Materials, (Kevin McGrath and David Kaplan, eds.), Birkhauser Press, 133-177, 1997.

27. Dan W. Urry, D. T. McPherson, J. Xu, H. Daniell, C. Guda, D. C. Gowda, Naijie Jing, T. M. Parker, "Protein-Based Polymeric Materials: Syntheses and Properties" in The Polymeric Materials Encyclopedia: Synthesis, Properties and Applications, CRC Press, Boca Raton, pp. 7263-7279, 1996.
28. Dan W. Urry, Chi-Hao Luan, and ShaoQing Peng, "Molecular Biophysics of Elastin Structure, Function and Pathology," in Proceedings of The Ciba Foundation Symposium No. 192, The Molecular Biology and Pathology of Elastic Tissues, John Wiley & Sons, Ltd., Sussex, UK., pp. 4-30, 1995.
29. Dan W. Urry, Larry C. Hayes and D. Channe Gowda, "Electromechanical Transduction: Reduction-driven Hydrophobic Folding Demonstrated in a Model Protein to Perform Mechanical Work," *Biochem. Biophys. Res. Comm.* **204**, 230-237, 1994.
30. Dan W. Urry, "Elastic Biomolecular Machines: Synthetic chains of amino acids, patterned after those in connective tissue, can transform heat and chemical energy into motion," *Scientific American*, January 1995, 64-69.
31. Dan W. Urry and Chi-Hao Luan, "A New Hydrophobicity Scale and Its Relevance to Protein Folding and Interactions at Interfaces," in Proteins at Interfaces 1994, American Chemical Society Symposium Series, (Thomas A. Horbett and John L. Brash, editors), pp. 92-110, Washington, D.C., 1995.
32. D. W. Urry, "Postulates for Protein (Hydrophobic) Folding and Function," *Int. J. Quant. Chem.: Quant. Biol. Symp.* **21**, 3-15, 1994.
33. Dan W. Urry, David T. McPherson, Jie Xu, D. Channe Gowda, and Timothy M. Parker, "Elastic and Plastic Protein-based Polymers: Potential for Industrial Uses," in Industrial Biotechnological Polymers, (Chas. Gebelein and Chas. E. Carraher, Jr., editors), Technomic Publishing Co., Lancaster, PA, pp. 259-281, 1995.
34. Dan W. Urry, Alastair Nicol, David T. McPherson, Jie Xu, Peter R. Shewry, Cynthia M. Harris, Timothy M. Parker, and D. Channe Gowda, "Properties, Preparations and Applications of Bioelastic Materials," In Encyclopedic Handbook of Biomaterials and Bioengineering - Part A - Materials, Vol. 2, Marcel Dekker, Inc., New York, pp. 1619-1673, 1995.
35. Luke A. Strzegowski, Manuel Bueno Martinez, D. Channe Gowda, Dan W. Urry and David A. Tirrell, "Photomodulation of the Inverse Temperature Transition of a Modified Elastin Poly(Pentapeptide)," *J. Am. Chem. Soc.* **116**, 813-814, 1994.
36. Dan W. Urry, "Biophysics of Energy Converting Model Proteins," *Mat. Res. Soc. Symp. Proc.* 321-332, 1994.
37. Dan W. Urry, "Conversion of Available Energy Forms into Desired Forms by a Biologically Accessible Mechanism," In Nondestructive Characterization of Materials VI (Robert E. Green, Jr., Ed.), Proceedings of the Sixth International Symposium on Nondestructive Characterization of Materials, Oahu, Hawaii, Plenum Press, New York, NY, pp. 629-636, 1994.
38. D. C. Gowda, T. M. Parker, C. M. Harris, R. D. Harris and D. W. Urry, "Design and Synthesis of Poly-tricosapeptides to Enhance Hydrophobic-induced pKa Shifts," In Peptides: Chemistry, Structure and Biology

- (R. S. Hodges and J. A. Smith, Eds.), Proceedings of the Thirteenth American Peptide Symposium, Edmonton, Alberta, Canada, pp. 940-943, 1994.
39. Dan W. Urry, Shaoqing Peng, D. Channe Gowda, Timothy M. Parker, and R. Dean Harris, "Comparison of Electrostatic- and Hydrophobic-induced pKa Shifts in Polypentapeptides: The Lysine Residue," *Chemical Physics Letters* **225**, 97-103, 1994.
 40. Dan W. Urry, D. Channe Gowda, ShaoQing Peng, Timothy M. Parker, Naijie Jing and R. Dean Harris, "Nanometric Design of Extraordinary Hydrophobicity-induced pKa Shifts for Aspartic Acid: Relevance to Protein Mechanisms," *Biopolymers* **34**, 889-896, 1994.
 41. D. Channe Gowda, Timothy M. Parker, R. Dean Harris and Dan W. Urry, "Synthesis, Characterizations and Medical Applications of Bioelastic Materials," In Peptides: Design, Synthesis, and Biological Activity (Channa Basava and G. M. Anantharamaiah, Eds.), Birkhäuser, Boston, MA, pp. 81-111, 1994.
 42. Alastair Nicol, D. Channe Gowda, Timothy M. Parker and Dan W. Urry, "Elastomeric Polytetrapeptide Matrices: Hydrophobicity Dependence of Cell Attachment from Adhesive, (GGIP)_n, to Non-adhesive, (GGAP)_n, Even in Serum," *J. Biomed. Mater. Res.* **27**, 801-810, 1993.
 43. Dan W. Urry, D. Channe Gowda, Cynthia M. Harris and R. Dean Harris, "Bioelastic Materials and the DT_t-Mechanism in Drug Delivery," In Polymeric Drugs and Drug Administration (Raphael M. Ottenbrite, ed.), American Chemical Society Symposium Series 545, pp. 15-28, 1994.
 44. Dan W. Urry, ShaoQing Peng, Timothy M. Parker, D. Channe Gowda, and Roland D. Harris, "Relative Significance of Electrostatic- and Hydrophobic-Induced pK_a Shifts in a Model Protein: The Aspartic Acid Residue," *Angew. Chem. (German)* **105**, 1523-1525, 1993; *Angew. Chem. Int. Ed. Engl.* **32**, 1440-1442, 1993.
 45. Alastair Nicol, D. Channe Gowda, Timothy M. Parker, and Dan W. Urry, "Cell Adhesive Properties of Bioelastic Materials Containing Cell Attachment Sequences," In Biotechnol. Bioactive Polym. (Charles G. Gebelein and Charles E. Carraher, Jr., Eds.), Plenum Press, New York, pp. 95-113, 1994.
 46. Lynne D. Hoban, Marissa Pierce, Jerry Quance, Isaac Hayward, Adam McKee, D. Channe Gowda, Dan W. Urry and Taffy Williams, "The Use of Polypenta-peptides of Elastin in the Prevention of Postoperative Adhesions," *J. Surgical Res.* **56**, 179-183, 1994.
 47. Dan W. Urry, D. Channe Gowda, Betty A. Cox, Lynne D. Hoban, Adam McKee and Taffy Williams, "Properties and Prevention of Adhesions Applications of Bioelastic Materials," *Mat. Res. Soc. Symp. Proc.* **292**, 253-264, 1993.
 48. Dan W. Urry, ShaoQing Peng and Timothy M. Parker, "Delineation of Electrostatic-and Hydrophobic-Induced pKa Shifts in Polypentapeptides: The Glutamic Acid Residue," *J. Am. Chem. Soc.* **115**, 7509-7510, 1993.
 49. Dan W. Urry, Larry C. Hayes, Timothy M. Parker and R. Dean Harris, "Baromechanical Transduction in a Model Protein by the DT_t Mechanism," *Chem. Phys. Letters* **201**, 336-340, 1993.

50. Dan W. Urry, "Bioelastic Materials as Matrices for Tissue Reconstruction," In Tissue Engineering: Current Perspectives (Eugene Bell, Ed.), Birkhäuser Boston, Div. Springer-Verlag, New York, NY, pp. 199-206, 1993.
51. Dan W. Urry, Larry C. Hayes, D. Channe Gowda, Cynthia M. Harris, and R. Dean Harris, "Reduction-driven Polypeptide Folding by the DT_t Mechanism," *Biochem. Biophys. Res. Comm.* **188**, 611-617, 1992.
52. D. W. Urry, D. C. Gowda, S. Q. Peng, T. M. Parker, and R. D. Harris, "Design at Nanometric Dimensions to Enhance Hydrophobicity-induced pKa Shifts," *J. Am. Chem. Soc.* **114**, 8716-8717, 1992.
53. D. W. Urry, A. Nicol, D. C. Gowda, L. D. Hoban, A. McKee, T. Williams, D. B. Olsen and B. A. Cox, "Medical Applications of Bioelastic Materials," In Biotechnological Polymers: Medical, Pharmaceutical and Industrial Applications (Charles G. Gebelein, Ed.), Technomic Publishing Co., Inc., Atlanta, Georgia, pp. 82-103, 1993.
54. Dan W. Urry, "Molecular Machines: How Motion and Other Functions of Living Organisms Can Result from Reversible Chemical Changes," *Angew. Chem. (German)* **105**, 859-883, 1993; *Angew. Chem. Int. Ed. Engl.*, **32**, 819-841, 1993.
55. D. W. Urry, D. C. Gowda, C. Harris, R. D. Harris and B. A. Cox, "Development of Bioelastic Materials as Biocompatible, Transducible and Degradable Drug Delivery Matrices," *Polym. Preprints, Div. Polym. Chem., Am. Chem. Soc.*, **33** (2), 84-85, 1992.
56. Dan W. Urry, D. Channe Gowda, Timothy M. Parker, Chi-Hao Luan, Michael C. Reid, Cynthia M. Harris, Asima Pattanaik, and R. Dean Harris, "Hydrophobicity Scale for Proteins Based on Inverse Temperature Transitions," *Biopolymers* **32**, 1243-1250, 1992.
57. Chi-Hao Luan, Timothy M. Parker, D. Channe Gowda and Dan W. Urry, "Hydrophobicity of Amino Acid Residues: Differential Scanning Calorimetry and Synthesis of the Aromatic Analogues of the Polypentapeptide of Elastin," *Biopolymers* **32**, 1251-1261, 1992.
58. David T. McPherson, Casey Morrow, Daniel S. Minehan, Jianguo Wu, Eric Hunter, and Dan W. Urry, "Production and Purification of a Recombinant Elastomeric Polypeptide, G-(VPGVG)₁₉-VPGV, from *Escherichia coli*," *Biotechnol. Prog.* **8**, 347-352, 1992.
59. Frederick J. Elsas, D. Channe Gowda and Dan W. Urry, "Synthetic Polypeptide Sleeve for Strabismus Surgery," *J. Pediatr. Ophthalmol. Strabismus* **29**, 284-286, 1992.
60. Dan W. Urry, C.-H. Luan, S. Q. Peng, T. M. Parker and D. C. Gowda, "Hierarchical and Modulable Hydrophobic Folding and Self-assembly in Elastic Protein-based Polymers: Implications for Signal Transduction," *Mat. Res. Soc. Symp. Proc.* **255**, 411-422, 1992.
61. Dan W. Urry, "Molecular Engines and the ΔT_t Mechanism for Energy Conversion," Proceedings of Bionic Design International Workshop, Agency of Industrial Science and Technology, Ministry of International Trade and Industry (AIST, MITI), Japan, 9-12, 1992.

62. Dan W. Urry, "Free Energy Transduction in Polypeptides and Proteins Based on Inverse Temperature Transitions," *Prog. Biophys. Molec. Biol.* **57**, 23-57, 1992.
63. Dan W. Urry, Timothy M. Parker, Alastair Nicol, Asima Pattanaik, Daniel S. Minehan, D. Channe Gowda, Casey Morrow and David T. McPherson, "The Capacity to Vary the Bioactive Role of Elastic Protein-Based Polymers," (*Am. Chem. Soc.*), *Div. Polym. Mat.: Sci. and Eng.* **66**, 399-402, 1992.
64. D. W. Urry, "Protein Folding and the Movements of Life", *The World & I*, (Natural Science - AT THE EDGE) **6**, 301-309, 1991.
65. Dan W. Urry, Shao Qing Peng and Timothy M. Parker "Hydrophobicity-induced pK Shifts in Elastin Protein-Based Polymers," *Biopolymers* **32**, 373-379, 1992.
66. Dan W. Urry, Larry C. Hayes, D. Channe Gowda, and Timothy M. Parker, "Pressure Effect on Inverse Temperature Transitions: Biological Implications," *Chem. Phys. Letters.* **182**, 101-106, 1991.
67. Chi-Hao Luan and Dan W. Urry, "Solvent Deuteration Enhancement of Hydrophobicity: DSC Study of the Inverse Temperature Transition of Elastin-based Polypeptides," *J. Phys. Chem.* **95**, 7896-7900, 1991.
67. Dan W. Urry, "Elastin: Structure, Mechanism, Function, Pathology, and Materials Applications," Proceedings of the Fifth Annual Meeting Japan Society for Elastin Research, Tokyo, Japan, 1994 (in press).
68. Chi-Hao Luan and Dan W. Urry, "Molecular Mechanics Study of the β -spiral Conformations of the Phe⁴, Tyr⁴, and Trp⁴ Analogs of the Elastomeric Poly(Val¹-Pro²-Gly³-Val⁴-Gly⁵)," *Intl. J. Quant. Chem.* **42**, 1439-1448, 1992.
69. Chi-Hao Luan, D. K. Chang, Timothy M. Parker, N. Rama Krishna, and Dan W. Urry, " β -spiral Conformation of the Elastomeric Polytetrapeptides, (VPGG)_n and (IPGG)_n, by 2D NMR, and Molecular Mechanics Studies," *Intl. J. of Quant. Chem., Quant. Biol. Symp.* **18**, 183-198, 1991.
70. Dan W. Urry, C-H Luan, T. M. Parker, D. C. Gowda, K. U. Prasad, M. C. Reid, and A. Safavy, "Temperature of Polypeptide Inverse Temperature Transition Depends on Mean Residue Hydrophobicity," *J. Am. Chem. Soc.* **113**, 4346-4348, 1991.
71. Dan W. Urry, Timothy M. Parker, Michael C. Reid, and D. Channe Gowda, "Biocompatibility of the Bioelastic Materials, Poly(GVGVP) and Its γ -irradiation Cross-linked Matrix: Summary of Generic Biological Test Results," *J. Bioactive Compatible Polym.* **6**, 263-282, 1991.
72. Chi-Hao Luan, Tim Parker, Kari U. Prasad, and Dan W. Urry, "DSC Studies of NaCl Effect on the Inverse Temperature Transition of Some Elastin-based Polytetra-, Polypenta-, and Polynona peptides," *Biopolymers* **31**, 465-475, 1991.
73. D. W. Urry, "Thermally Driven Self-assembly, Molecular Structuring and Entropic Mechanisms in Elastomeric Polypeptides," In Mol. Conformation and Biol. Interactions (P. Balaram and S. Ramaseshan, Eds.) Indian Acad. of Sci., Bangalore, India, pp. 555-583, 1991.

74. D. W. Urry, "Protein Folding Controlled by Chemically Shifting the Temperatures of Inverse Temperature Transitions," In Proteins: Structure, Dynamics and Design (V. Renugopalakrishnan, P. R. Carey, I. C. P. Smith, S. G. Huang, and A. C. Storer, Eds.), Escom Sci. Publ. B.V., Leiden, The Netherlands, pp. 352-360, 1991.
75. D. W. Urry, "Bioelastic Materials as Chemomechanically Transducing ("Smart") Matrices for Drug Delivery," In Cosmetic and Pharmaceutical Applications of Polym. (C. G. Gebelein, T. C. Cheng, and V. C. Yang, Eds.), Plenum Press, New York, 181-192, 1991.
76. Alastair Nicol, D. Channe Gowda, and Dan W. Urry, "Elastic Protein-based Polymers as Cell Attachment Matrices," *J. Vasc. Surg.*, **13**, 746-748, 1991.
77. D. W. Urry, J. Jaggard, K. U. Prasad, T. Parker, and R. D. Harris, "Poly(Val¹-Pro²-Ala³-Val⁴-Gly⁵): A Reversible, Inverse Thermoplastic," In Biotechnology and Polymers (C. G. Gebelein, Ed.), Plenum Press, New York, 265-274, 1991.
78. Dan W. Urry and Camille Sandorfy, "Chemical Modulation of Transmembrane Protein Structure and Function," In Advances in Membr. Fluidity Vol. 5, Drug and Anesthetic Effects on Membr. Structure and Function (R. C. Aloia, C. C. Curtain, and L. M. Gordon, Eds.), Wiley-Liss, Inc., New York, NY, 91-131, 1991.
79. D. W. Urry, "Preprogrammed Drug Delivery Systems Using Chemical Triggers for Drug Release by Mechanochemical Coupling," *AM. CHEM. SOC., DIV. POLYM. MAT.: SCI. AND ENG.* **63**, 329-336, 1990.
80. D. W. Urry, "Elastomeric Polypeptide Biomaterials: Structure and Free Energy Transduction," *Mat. Res. Soc. Symp. Proc.* **174**, 243-250, 1990.
81. Dan. W. Urry, Shao Qing Peng, Larry Hayes, John Jaggard and R. Dean Harris, "A New Mechanism of Mechanochemical Coupling: Stretch-Induced Increase in Carboxyl pK_a as a Diagnostic," *Biopolymers* **30**, 215-218, 1990.
82. Dan W. Urry, C-H. Luan, R. Dean Harris and Kari U. Prasad, "Aqueous Interfacial Driving Forces in the Folding and Assembly of Protein (Elastin)-Based Polymers: Differential Scanning Calorimetry Studies," *Polym. Preprints, Div. Polym. Chem., Am. Chem. Soc.* **31**, 188-189, 1990.
83. Dan W. Urry, "General Properties and Applications of Sequential Polypeptides from Elastin and Their Analogs," *Am. Chem. Soc., Div. Polym. Mat.: Sci. and Eng.* **62**, 587-593, 1990.
84. Chi-Hao Luan, R. Dean Harris, Kari U. Prasad, and Dan W. Urry, "DSC Studies of the Inverse Temperature Transition of the Polypentapeptide of Elastin and Its Analogues," *Biopolymers* **29**, 1699-1706, 1990.
85. Dan W. Urry "Protein Folding and Assembly: An Hydration-Mediated Free Energy Driving Force," In Protein Folding: Deciphering the Second Half of the Genetic Code, (Lila Gierasch and Johnathan King, Eds.), Am. Assoc. for the Advancement of Sci., Washington, D. C., 63-71, 1990.

86. Dan W. Urry, "Protein Folding and Assembly: An Hydration-Mediated 5. D. K. Chang and D. W. Urry, "Polypentapeptide of Elastin: Damping of Internal Chain Dynamics on Extension," *J. Computational Chem.* **10**, 850-855, 1989.
87. D. K. Chang, and Dan W. Urry, "The Molecular Dynamics of the β -Spiral of the Polypentapeptide of Elastin in "State III" with 2.9 Pentamers/Turn," Special Issue in Honor of Prof. Per Olov Löwdin, *J. Mol. Structure (Theochem)* **199**, 303-312, 1989.
88. D. K. Chang, C. M. Venkatachalam, K. U. Prasad and D. W. Urry, "Nuclear Overhauser Effect and Computational Characterization of the β -Spiral of the Polypentapeptide of Elastin," *J. of Biomol. Structure & Dynamics*. **6**, 851-858, 1989.
89. H. Zhang, K. U. Prasad and D. W. Urry, "Synthesis of 4% Glu-Containing Val¹ and Ile¹-polypentapeptides: Model Protein Systems for Demonstrating Mechanochemical Coupling," *J. Protein Chem.* **8**, 173-182, 1989.
90. D. W. Urry, D. K. Chang, R. Krishna, D. H. Huang, T. L. Trapane, and K. U. Prasad, "Two Dimensional Proton Nuclear Magnetic Resonance Studies on Poly(VPGVG) and its Cyclic Conformational Correlate, Cyclo(VPGVG)₃," *Biopolymers* **28**, 819-833, 1989.
91. A. Killian, B. Kruijff and D. W. Urry, "A Mismatch Between the Length of Gramicidin and the Lipid Chains is a Prerequisite for H_{II} Phase Formation in Phosphatidylcholine Model Membranes," *Biochim. Biophys. Acta* **978**, 341-345, 1989.
92. D. K. Chang and D. W. Urry, "Polypentapeptide of Elastin: Damping of Internal Chain Dynamics on Extension," *J. Computational Chem.* **10**, 850-855, 1989.